Production Description

Name	Isolation Coveralls with Hood
Material	PP+PE Coating
Weight	50-65GSM
MOQ	10,000PCS
Packing	Normally,1pcs/polybag, 50pcs/ctn
Delivery	Within 2 weeks
features	Breathable coverall fabric Front long zipper,elastic cuffs/waist and attached hood

*Application

COMMON USES in clinics, hospitals, laboratories, workshops, etc. For general isolation and protection.

*Safety and Anti-Epidemic Medical-Grade Fabric

Lightweight multi-ply material that is fluid-resistant and breathable Safe and strong enough for personal protection Gowns are generously sized for full coverage With elastic or knit cuffs

*











检测报告



正本

武汉海关技术中心

Technology Center Of Wuhan Customs District

检测报告

Report Test

申报样品名称:一次性隔离衣(非医用)

Name of sample declared: Disposable isolation gown(non-medical use

报告编号(No.of Series): 21202000746-1

报告日期 (Date): 2020-05-15

报告页数 (Page): 共 1 页 第 1 页

委托人: 湖北君橙服饰有限公司

Consignor: HUBEI ORANGE FASHION CO.,LTD

样品来源:委托人送样

Origin of sample: Delivering by Consignor

检测项目及结果:

Item inspected and its data:

接样日期: 2020-05-12

Date of reception:

检测依据:

GB 15979-2002 附录 B

Method of inspection:

样品标记 Sample Mark	2#	
样品编号 Sample No.	202003069	
细菌菌落总数 Total bacterial count (CFU/g)	84	
大肠菌群 Coliforms	未检出 ND	

以下空白 BLANK BELOW



签署(Signature):

印章 (Seal): Notice:1.本报告仅对到样负责。(It is only responsible for the sample received.)

2.未加盖检验检测报告专用章无效。(It is invalid without original seal of inspection & test report.)

3.未经本中心书面许可,不得部分复制报告。(It can not be copied separately without authorized permission.) 地址: 湖北省武汉市汉阳琴台大道 588 号

Add.: No.588Qin Tai Avenue, Hanyang, Wuhan, Hubei Province of P.R.C

电话 (Tel): 027-58905910; 58905912

传真 (Fax): 027-58905911















检验检测报告

(电子版)

防伪查询网址: www.gttc.net.cn 防伪码: OEIM-8603-54

共3页 第1页





地址:湖北省武汉市江汉区淮海路泛海国际S0H0城8号楼1506室 委托单位 -次性隔离衣(非医用) 商标: BECOLOR 批号款号: 批号: 20200516 款号: CF23156 客户认定 信息 颜色: 浅蓝 材质: 100%聚丙烯

号型规格: OFSPC-XL 生产单位: 湖北君橙服饰有限公司

检验性质 样品受理/测试开始日期 2020-05-17 报告签发日期 2020-05-23 委托检测 Q/0FGLY01-2020 《一次性隔离衣(非医用)》

判定依据

综合检验 结论

检验 结

金測 果 新观品:	检验检测项目	判定依据	判定
料 断裂强	h	Q/0FGLY01-2020	符合
断裂伸	长率	Q/0FGLY01-2020	符合
抗渗水	生	Q/0FGLY01-2020	符合

备注

本报告中檢验检测项目均在相应标准规定的环境条件下进行(有注明的除外)。 复印件、副本未重新加盖报告书确认章无效。 本报告检验检测地址为广州市番禺区珠江路1号。

签发: 刘圆 工程师

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

电话:020-61994598/61994599

电话:020-37721161







样品图片

(电子版)

No:200128094



总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

电话:020-61994598/61994599 电话:020-37721161







检验检测报告附页

(电子版)

No:200128094

共3页 第3页

检验检测项目 (计量单位)	测试方法	标准值及允差	检验检测结果	判定	备注
[样品识别] ●断裂强力(N)	GB/T 3923.1-2013 夹距:100mm 速度:100mm/min	纵向 ≥10 横向 ≥10	纵向 49 横向 95	符合	注
●断裂伸长率(%)	GB/T 3923.1-2013 夹距:100mm 速度:100mm/min	纵向 ≥15 横向 ≥15	纵向 101 横向 115	符合	注
●抗渗水性 (cmH ₂ 0)	GB/T 4744-2013 增压法:60cmH ₂ 0/min 水温:20.0°C 正面向下接触水面	≥10	1# 71.3 2# 73.9 3# 36.4 4# 64.5 5# 68.6 平均值 62.9	符合	注

注: 判定指标来源于客户要求的企业标准(Q/OFGLY01-2020)。我单位获CMA认定授权的检验能力覆盖Q/OFGLY01-2020所检项目。

注

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

——本报告结束——

电话:020-61994598/61994599 电话:020-37721161