
Name	SMS Isolation Gown China Factory
Material	Spunbond + Meltblown + Spunbond Nonwovens
Weight	40GSM
MOQ	10,000PCS
Packing	Normally,1pcs/polybag, 50pcs/ctn
Delivery	Within 2 weeks
Features	Waterproof/non-sterile


#### \*Application

COMMON USES in clinics, hospitals, laboratories, workshops, etc. For general isolation and protection.


#### \*Safety and Anti-Epidemic Medical-Grade Fabric

Lightweight multi-ply material that is fluid-resistant and breathable Safe and strong enough for personal protection Gowns are generously sized for full coverage With waist and neck ties to ensure secure fit With elastic or knit cuffs













# 检测报告



### 正本

## 武汉海关技术中心

## Technology Center Of Wuhan Customs District

#### 检测报告

Report Test

申报样品名称:一次性隔离衣(非医用)

Name of sample declared: Disposable isolation gown(non-medical use

报告编号(No.of Series): 21202000746-1

报告日期 (Date): 2020-05-15

报告页数 (Page): 共 1 页 第 1 页

委托人: 湖北君橙服饰有限公司

Consignor: HUBEI ORANGE FASHION CO.,LTD

样品来源:委托人送样

Origin of sample: Delivering by Consignor

检测项目及结果:

Item inspected and its data:

接样日期: 2020-05-12

Date of reception:

检测依据:

GB 15979-2002 附录 B

Method of inspection:

样品标记 Sample Mark	2#	
样品编号 Sample No.	202003069	
细菌菌落总数 Total bacterial count (CFU/g)	84	
大肠菌群 Coliforms	未检出 ND	

以下空白 BLANK BELOW



签署(Signature):

印章 (Seal): Notice:1.本报告仅对到样负责。(It is only responsible for the sample received.)

2.未加盖检验检测报告专用章无效。(It is invalid without original seal of inspection & test report.)

3.未经本中心书面许可,不得部分复制报告。(It can not be copied separately without authorized permission.) 地址: 湖北省武汉市汉阳琴台大道 588 号

Add.: No.588Qin Tai Avenue, Hanyang, Wuhan, Hubei Province of P.R.C

电话 (Tel): 027-58905910; 58905912

传真 (Fax): 027-58905911















#### 检验检测报告

(电子版)

防伪查询网址: www.gttc.net.cn 防伪码: OEIM-8603-54

共3页 第1页





地址:湖北省武汉市江汉区淮海路泛海国际S0H0城8号楼1506室 委托单位 -次性隔离衣(非医用) 商标: BECOLOR 批号款号: 批号: 20200516 款号: CF23156 客户认定 信息 颜色: 浅蓝 材质: 100%聚丙烯

号型规格: OFSPC-XL 生产单位: 湖北君橙服饰有限公司

检验性质 样品受理/测试开始日期 2020-05-17 报告签发日期 2020-05-23 委托检测 Q/0FGLY01-2020 《一次性隔离衣(非医用)》

判定依据

综合检验 结论

检验 结

金測 果 断观品 7	检验检测项目	判定依据	判定
果 断裂强力		Q/0FGLY01-2020	符合
断裂伸七	长率	Q/0FGLY01-2020	符合
抗渗水性	ŧ	Q/0FGLY01-2020	符合

备注

本报告中檢验检测项目均在相应标准规定的环境条件下进行(有注明的除外)。 复印件、副本未重新加盖报告书确认章无效。 本报告检验检测地址为广州市番禺区珠江路1号。

签发: 刘圆 工程师

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

电话:020-61994598/61994599

电话:020-37721161







# 样品图片

(电子版)

No:200128094



总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

电话:020-61994598/61994599 电话:020-37721161







### 检验检测报告附页

(电子版)

No:200128094

共3页 第3页

检验检测项目 (计量单位)	测试方法	标准值及允差	检验检测结果	判定	备注
[样品识别] ●断裂强力(N)	GB/T 3923.1-2013 夹距:100mm 速度:100mm/min	纵向 ≥10 横向 ≥10	纵向 49 横向 95	符合	注
●断裂伸长率(%)	GB/T 3923.1-2013 夹距:100mm 速度:100mm/min	纵向 ≥15 横向 ≥15	纵向 101 横向 115	符合	注
●抗渗水性 (cmH <sub>2</sub> 0)	GB/T 4744-2013 增压法:60cmH <sub>2</sub> 0/min 水温:20.0°C 正面向下接触水面	≥10	1# 71.3 2# 73.9 3# 36.4 4# 64.5 5# 68.6 平均值 62.9	符合	注

注: 判定指标来源于客户要求的企业标准(Q/OFGLY01-2020)。我单位获CMA认定授权的检验能力覆盖Q/OFGLY01-2020所检项目。

注

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号

——本报告结束——

电话:020-61994598/61994599 电话:020-37721161